



Specification

Nominal Voltage (V)	6V (3 cells in series)	
Rated Capacity	3.2Ah	(C ₂₀ , 1.75V/cell)
Dimensions(mm)	Length	125.5 ± 2 mm
	Width	33.5 ± 1 mm
	Height	60 ± 1.5 mm
	Total Height	66 ± 1.5 mm
Nominal Capacity @25°C (Ah)	20 Hour rate (0.162A to 5.25 volts)	3.24Ah
	10 Hour rate (0.309A to 5.25 volts)	3.09Ah
	5 Hour rate (0.552A to 5.25 volts)	2.76Ah
	1 Hour rate (2.080A to 4.80 volts)	2.08Ah
	15 min rate (6.160A to 4.80 volts)	1.54Ah
Approx. Weight	0.62 kg	
Terminal	T1-A	
Max.Discharge Current	48A @25°C (5s)	
Internal Resistance	18mΩ @25°C (Full Charged Battery)	
Floating Design Life	5 years @25°C	
Ambient Temperature	Charge: -15°C~50°C	
	Discharge: -20°C~60°C	
	Storage: -20°C~50°C	
Container Material	A.B.S , UL94-HB , UL94-V0 , Optional	
Self Discharge	VRLA batteries can be stored for more than 6 months at 25°C. Self-Discharge ratio less than 3% per month at 25°C. Please charge batteries before using.	



Certification




Constant Current Discharge Characteristics (A), (25°C)

F.V/TIME	5min	10min	15min	30min	60min	2H	3H	5H	8H	10H	20H
1.60V/cell	12.62	8.272	6.160	3.280	2.080	1.172	0.837	0.564	0.374	0.320	0.171
1.70V/cell	11.46	7.664	5.808	3.184	2.034	1.154	0.816	0.556	0.368	0.312	0.165
1.75V/cell	10.29	7.184	5.488	3.088	2.008	1.144	0.808	0.552	0.365	0.309	0.162
1.80V/cell	9.232	6.720	5.168	2.992	1.979	1.134	0.798	0.546	0.360	0.304	0.155


Constant Wattage Discharge Characteristics (Watt), (25°C)

F.V/TIME	5min	10min	15min	30min	60min	2H	3H	5H	8H	10H	20H
1.60V/cell	22.83	15.10	11.34	6.259	4.125	2.324	1.668	1.126	0.746	0.639	0.342
1.70V/cell	21.10	14.24	10.89	6.129	4.050	2.298	1.629	1.110	0.735	0.624	0.331
1.75V/cell	19.20	13.59	10.38	5.996	4.003	2.280	1.615	1.103	0.729	0.618	0.325
1.80V/cell	17.39	12.82	9.862	5.859	3.949	2.263	1.597	1.091	0.720	0.609	0.312


Charge Characteristics Curve




Discharge Characteristics Curve



Cycle service life in relation to depth of discharge



Capacity Storage Characteristics



Capacity Factors with Different Temperature

Battery type		-20℃	-10℃	0℃	5℃	10℃	20℃	25℃	30℃	40℃	45℃
GEL Battery	6V&12V	50%	70%	83%	85%	90%	98%	100%	102%	104%	105%
	2V	60%	75%	85%	88%	92%	99%	100%	103%	105%	106%
AGM Battery	6V&12V	46%	66%	76%	83%	90%	98%	100%	103%	107%	109%
	2V	55%	70%	80%	85%	92%	99%	100%	104%	108%	110%

Maintenance & Cautions

☑ Charging Procedure:

Application	Charging method	Charge voltage at 25℃	Temperature compensation coefficient of charging voltage	Max.charging current	Temperature
For standby power source	Constant voltage charging (With current restriction)	2.25~2.30 V/cell	-3mV/℃/cell	0.2CA	-15~50℃
For cycle service		2.45~2.50 V/cell	-4mV/℃/cell	0.3CA	

☑ Every month, recommend inspection every battery voltage.

☑ Every three months, recommend equalization charge for one time. **Equalization charge method:**

Step 1: Discharge: 100% rate capacity discharge.

Step 2: Charge: Max. Current 0.3CA, constant voltage 2.45~2.50V/Cell charge 24h.

☑ Length of service life will be directly affected by the number of discharge cycles, depth of discharge, Ambient temperature and charging voltage.

☑ Charge the batteries at least once every six months, if they are stored at 25℃. **Charging Method:**

Constant Voltage : $-0.2C \times 2h + 2.4 \sim 2.45V/cell \times 24h$, Max. Current 0.25CA

Constant Current : $-0.2C \times 2h + 0.1C \times 12h$

Fast : $-0.2C \times 2h + 0.3C \times 4h$

☑ Terminal of torque:

Bolt	M5	M6	M8
Terminal	T3、T10	T4、T7、T11、T12、T13	T5、T6、T8、T9、T14
Torque	6~7N.m	8~10N.m	10~12N.m